


LAMIERE

sezione mm	laminato a freddo	laminato a caldo
	peso kg/m ²	peso kg/m ²
0,5	4,00	—
0,6	4,80	—
0,7	5,50	—
0,8	6,40	—
1,0	8,00	—
1,2	9,60	—
1,5	12,00	—
2,0	16,00	16,00
2,5	20,00	20,00
3,0	24,00	24,00
4,0	32,00	32,00
5,0	—	40,00
6,0	—	48,00
8,0	—	64,00
10,0	—	80,00
12,0	—	96,00

qualità AISI 304-316

TUBI QUADRI

 sezione mm	Spessore								
	1,0 mm	1,2 mm	1,5 mm	2,0 mm	2,5 mm	3,0 mm	4,0 mm	5,0 mm	6,0 mm
10 x 10	0,294								
12 x 12	0,358								
15 x 15	0,453	0,538	0,661						
16 x 16	0,485	0,576	0,709	0,920					
18 x 18	0,549	0,653	0,805						
20 x 20	0,613	0,729	0,900	1,175					
25 x 25	0,772	0,921	1,140	1,494	1,846	2,179			
30 x 30	0,932	1,112	1,379	1,813	2,222	2,645			
35 x 35	1,091	1,303	1,618	2,132	2,629	3,118			
40 x 40	1,251	1,495	1,857	2,451	3,036	3,602	4,708		
45 x 45	1,410	1,686	2,097	2,770	3,433	4,081	5,309		
50 x 50	1,570	1,878	2,336	3,089	3,818	4,559	5,960		
60 x 60			2,814	3,727	4,607	5,516	7,222		
80 x 80			3,771	5,003	6,203	7,430	9,807	12,095	
100 x 100			4,728	6,279	7,918	9,343	12,358	15,322	18,236
120 x 120				7,555		11,257	14,910	18,512	22,064
150 x 150				9,469		14,129	18,738	23,297	27,806
175 x 175				11,064		16,521	21,928	27,285	32,592

peso teorico chilogrammi per metro